

TECHNICAL INFORMATION

Productname : VALIREX Cu 8 % naphthenate (low leach)

Date of issue : June 12, 2002

Description copper naphthenate

Use fungicide for wood preservatives, PVC compounding etc.

| Specifications | method of analysis | minimum | Maximum |
|-----------------------------------|--------------------|------------|---------|
| metal content (%) | EDTA | 7.8 | 8.2 |
| Colour | | Dark green | |
| density (kg/m ³ -20°C) | ISO 2811 | 1000 | 1040 |
| viscosity (St-25°C) | ASTM D445-72 | 20 | - |
| flash point (°C) | ASTM D93-72 | 101 | - |

Some standard methods of analysis have been slightly modified.

Compatibility most drying oils, alkyd resins, fungicides and other ingredients of wood preservatives, except PCP; to be tested in PVC

Packaging 200 l (55 gals) and 60 l (15 gals) steel drums, bulk

Note Use as biocide only in accordance with compulsory legal prescriptions

The safety data sheet is available on request

Notice

The presented information is accurate to the best of our knowledge, but without any guarantee. Users should satisfy themselves on the suitability of this product for their purposes. If necessary, they can consult our technical service staff.

This issue supersedes and cancels all previous issues concerning this product.

Umicore Specialty Materials Brugge NV

Kleine Pathoekeweg 82
Be-3000 Brugge Belgium

Tel +32.50.320.720
Fax +32.50.316.047

www.csm.umicore.com
info.USMBrugge@eu.umicore.com